

Cold Rolled Magnetic Lamination Semi-Processed (SP) ASTM A726-05

Trade Names	ASTM Type	Core Loss by Thickness Watts/lb 15 Kilogausses 60HZ		Typical Core Loss Watts/lb	Typical Permeability
		Thick	Max w/lb		
	47D175 64D260	.0185 .0250	1.75 2.60	1.70 1.85	2100 2100
M-50	47D190 64D290	.0185 .0250	1.90 2.90	1.90 2.60	2200 2200
M-55	47D270 64D360	.0185 .0250	2.70 3.60	2.30 3.10	2600 2600
M-56	47D330 64D430 71D480 79D540	.0185 .0250 .0280 .0310	3.30 4.30 4.80 5.40	2.90 3.50 4.00 5.00	2400 2700 2700 2700